

GEL Series Battery

Range Summary

By combining the newly developed nano gel electrolyte with high density paste, Vvution created an innovative range of VTG batteries. The range offers high recharge efficiency at the very low charge current. The acid stratification is highly depressed by adding of gel. This range battery is highly suited to energy storage for renewable energy such as PV and wind turbine power systems applications.

Application


- Photovoltaic system
- Renewable Energy System
- Electric Utility
- Outdoor control Equipment
- Railroad Utility

General Features


- 12 years float life at 20°C
- Up to 5 years design life at renewable energy applications
- Wide operating temperature range of -15 to 60°C
- Nano gel electrolyte eliminate the acid stratification and prolong cycle life
- Round trip efficiency as high as 85%
- Thick positive flat plate with high density paste
- Low self-discharge rate and long shelf life(1 year at 25°C)
- Excellent deep discharge recovery capability

Construction


- PositiveLead dioxide
- NegativeLead
- Container.....ABS
- CoverABS
- SealantEpoxy Resin
- Safety valveEPDR
- TerminalCopper
- SeparatorAGM
- ElectrolyteAcid with gel



Terminal Dimensions



Battery Model	VTG 12-80			
Designed Floating Life	12 Years			
Designed Cycle Life	5 Years			
Capacity(20°C)	10HR(8A,1.80V)	24HR(4A,1.80V)	48HR(2.08A,1.80V)	100HR(1.08A,1.80V)
	80Ah	85Ah	89Ah	96Ah
Dimensions	Length	Width	Height	Total Height
	260mm(10.2inch)	168mm(6.62inch)	211mm(8.31inch)	214mm(8.43inch)
Approx. Weight	24Kg			
Internal Resistance	Full charged at 20°C: 0.006 Ohm			
Self Discharge	3% of capacity declined per month at (20°C)			
Capacity Affected by Temp.(10HR)	40°C	20°C	0°C	-15°C
	109%	100%	85%	65%
Charge Voltage(20°C)	Cycle use		Float use	
	14.4-14.8V(-30mV/ °C), max. Current: 20A		13.6-13.8V(-18mV/ °C)	



Constant current discharge ratings-amperes at 20°C

TIME	1h	3h	5h	10h	24h	48h	72h	100h	120h
CUT-OFF VOLTAGE	1.80	1.80	1.80	1.80	1.80	1.80	1.80	1.80	1.80
CAPACITY(Ah)	50	60	68	80	85	89	93	96	98

Quality Management System
Authentication
GB/T19001-2008
NO.00113Q22865FROM/4200

CE authentication
CE12-GPE 120171

